


AMENDMENTS TO THE CLAIMS


This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:


1. (currently amended): A polymeric fluorescent substance exhibiting fluorescence in the solid state, having a polystyrene reduced number-average molecular weight of 1×10^3 to 1×10^8 , and comprising one or more repeating units of formula (1) and one or more repeating units of formula (8),




in the formula, Ar_1 is a divalent group represented by one of the following formulae (2) to (7); R_1 and R_2 each independently represent a group selected from a hydrogen atom, alkyl groups, aryl groups, monovalent heterocyclic compound groups and cyano group; and n is 0 or 1,




(2)




(3)




(4)



(5)




(6)



(7)

in the formulae (2) to (7), X_1 , X_3 , X_5 , X_7 and X_9 each independently represent a group selected from $-CR_{21}=CR_{22}-$, $-CR_{23}=N-$, $-N=CR_{24}-$, $-O-CO-$, $-CR_{25}R_{26}-$, $-CO-$, $-O-$, $-S-$, $-Se-$, $-NR_{27}-$ and $-SiR_{28}R_{29}-$; X_2 , X_4 , X_6 , X_8 and X_{10} to X_{13} each independently represent a group selected from $-CR_{30}=$ and $-N=$; R_3 to R_{30} each independently represent a hydrogen atom or a substituent selected from alkyl group, alkoxy group, alkylthio group, alkylsilyl group, alkylamino group, ~~aryl group~~


alkylphenyl group, alkoxyphenyl group, aryloxy group, arylsilyl group, arylamino group, arylalkyl group, arylalkoxy group, arylalkylsilyl group, arylalkylamino group, arylalkenyl group, arylalkynyl ~~arylalkinyl~~ group, monovalent heterocyclic compound group and cyano group; at least one of R₃ to R₃₀ is not a hydrogen atom,



~~in~~ⁱⁿ the formula, Ar₂ represents an arylene group or divalent heterocyclic compound group, but the group is not represented by any of formulae (2) to (7); Ar₂ may have one or more substituents; when Ar₂ has a plurality of substituents, they may be the same or different; R₃₆ and R₃₇ each independently represent a group selected from a hydrogen atom, alkyl groups, aryl groups, monovalent heterocyclic compound groups and a cyano group; and ~~n~~ⁿ represents 0 or 1.


2. (currently amended): The polymeric fluorescent substance according to claim 1 wherein Ar₁ in formula (1) has one or more substituents selected from an ~~aryl group~~ alkylphenyl group, alkoxyphenyl group and a monovalent heterocyclic compound group.

3. (original): The polymeric fluorescent substance according to claim 1 or 2 wherein Ar₁ in formula (1) is represented by formula (1'),



in the formula, R_1' and R_2' represent each independently a group selected from alkyl group, alkoxy group, alkylthio group, alkylsilyl group, alkylamino group, aryl group, aryloxy group, arylsilyl group, arylamino group, arylalkyl group, arylalkoxy group, arylalkylsilyl group, arylalkylamino group, arylalkenyl group, arylalkynyl group, monovalent heterocyclic compound group, and cyano group; m' and n' are integers of 0-3 each independently; ~~however~~However, m' and n' are not 0 simultaneously; when m' is two or more, two or more R_1' may be the same or different; when n' is two or more, a plurality of R_2' may be the same or different; moreover, R_1' and R_2' may be connected to form a ring.


4. (original): The polymeric fluorescent substance according to claim 1 or 2 wherein Ar_2 in formula (8) is represented by formula (2'),



in the formula, R_3' and R_4' represent independently a group selected from a hydrogen atom, alkyl group, aryl group, and a heterocyclic compound group; R_5' and R_6' show each independently a group selected from alkyl group, alkoxy group, alkylthio group, alkylsilyl group, alkylamino group, aryl group, aryloxy group, arylsilyl group, arylamino group, arylalkyl group, arylalkoxy group, arylalkylsilyl group, arylalkylamino group, arylalkenyl group, arylalkynyl group, monovalent heterocyclic compound group, and cyano group; k' and l' are integers of 0-3 each independently; when k' is two or more, a plurality of R_5' may be the same or different; when l' is


two or more, plurality of R_6' may be the same or different; R_3' - R_6' may be connected to form a ring.

5. (currently amended): The polymeric fluorescent substance according to claim 1 or 2 wherein Ar_1 in formula (1) is represented by formula (1'),



in the formula, R_1' and R_2' represent each independently a group selected from alkyl group, alkoxy group, alkylthio group, alkylsilyl group, alkylamino group, aryl group, aryloxy group, arylsilyl group, arylamino group, arylalkyl group, arylalkoxy group, arylalkylsilyl group, arylalkylamino group, arylalkenyl group, arylalkynyl group, monovalent heterocyclic compound group, and cyano group; m' and n' are integers of 0-3 each independently; however, m' and n' are not 0 simultaneously; when m' is two or more, two or more R_1' may be the same or different; when n' is two or more, a plurality of R_2' may be the same or different; moreover, R_1' and R_2' may be connected to form a ring,

and Ar_2 of formula (8) is represented by formula (2')



in the formula, R_3' and R_4' represent independently a group selected from a hydrogen atom, alkyl group, aryl group, and a heterocyclic compound group; R_5' and R_6' show each independently a group selected from alkyl group, alkoxy group, alkylthio group, alkylsilyl group, alkylamino group, aryl group, aryloxy group, arylsilyl group, arylamino group, arylalkyl group, arylalkoxy group, arylalkylsilyl group, arylalkylamino group, arylalkenyl group, arylalkynyl group, monovalent heterocyclic compound group, and cyano group; k' and l' are integers of 0-3 each independently; when k' is two or more, a plurality of R_5' may be the same or different; when l' is two or more, plurality of R_6' may be the same or different; R_3' - R_6' may be connected to form a ring.

6. (original): The polymeric fluorescent substance according to claim 1 or 2 wherein the total amount of repeating units represented formulae (1) and (8) is 50 mol % or more based on the total amount of all repeating units, and the amount of repeating units represented by formula (1) is 0.1 mol % or more and 95 mol % or less based on the total amount of the repeating units represented by formulae (1) and (8).

7. (original): The polymeric fluorescent substance according to claim 1 or 2 wherein the total amount of repeating units represented by formulae (1) and (8) is 50 mol % or more based on the total amount of all repeating units, and the amount of repeating units represented by

the formula (1) is 5 mol % or more and 95 mol % or less based on the total amount of the repeating units represented by the formulae (1) and (8).

8. (currently amended): A polymer light emitting device comprising at least a light emitting layer between a pair of electrodes composed of an anode and a cathode at least one of which is transparent or semi-transparent wherein the light emitting layer comprises a polymeric fluorescent substance according to claim 1 ~~or 2~~.

9. (currently amended): The polymer light emitting device according to claim 8, further comprising a layer comprising a conducting polymer disposed between one electrode and the light emitting layer such that the layer containing a conducting polymer is adjacent to said electrode.

10. (original): The polymer light emitting device according to claim 8, further comprising an insulation layer having a thickness of 2 nm or less disposed between one electrode and the light emitting layer such that the insulation layer is adjacent to said electrode.

11. (original): The polymer light emitting device according to any one of claims 8 to 10, further comprising a layer comprising an electron transporting compound disposed between the cathode and the light emitting layer such that the layer comprising an electron transporting compound is adjacent to said light emitting layer.

12. (original): The polymer light emitting device according to any one of claims 8 to 10, further comprising a layer comprising a hole transporting compound disposed between the anode and the light emitting layer such that the layer comprising a hole transporting compound is adjacent to said light emitting layer.

13. (currently amended): The polymer light emitting device according to any one of claims 8 to 10, further comprising a layer comprising an electron transporting compound disposed between the cathode and the light emitting layer and a layer comprising a hole transporting compound disposed between the ~~cathode~~ anode and the light emitting layer such that the layer comprising an electron transporting compound is adjacent to said light emitting layer, and the layer comprising a hole transporting compound is adjacent to said light emitting layer.

14. (original): A flat light source comprising the polymer light emitting device of any one of claims 8 to 10.

15. (original): A segment display comprising the polymer light emitting device of any one of claims 8 to 10.

16. (original): A dot matrix display comprising the polymer light emitting device of any one of claims 8 to 10.

17. (original): A liquid crystal display comprising the polymer light emitting device of any one of claims 8 to 10 as a back-light.

18. (new): A polymer light emitting device comprising at least a light emitting layer between a pair of electrodes composed of an anode and a cathode at least one of which is transparent or semi-transparent wherein the light emitting layer comprises a polymeric fluorescent substance according to claim 2.

19. (new): The polymer light emitting device according to claim 18, further comprising a layer comprising a conducting polymer disposed between one electrode and the

light emitting layer such that the layer containing a conducting polymer is adjacent to said electrode.

20. (new): The polymer light emitting device according to claim 18, further comprising an insulation layer having a thickness of 2 nm or less disposed between one electrode and the light emitting layer such that the insulation layer is adjacent to said electrode.

21. (new): The polymer light emitting device according to any one of claims 18 to 20, further comprising a layer comprising an electron transporting compound disposed between the cathode and the light emitting layer such that the layer comprising an electron transporting compound is adjacent to said light emitting layer.

22. (new): The polymer light emitting device according to any one of claims 18 to 20, further comprising a layer comprising a hole transporting compound disposed between the anode and the light emitting layer such that the layer comprising a hole transporting compound is adjacent to said light emitting layer.

23. (new): The polymer light emitting device according to any one of claims 18 to 20, further comprising a layer comprising an electron transporting compound disposed between the anode and the light emitting layer and a layer comprising a hole transporting compound disposed between the cathode and the light emitting layer such that the layer comprising an electron transporting compound is adjacent to said light emitting layer, and the layer comprising a hole transporting compound is adjacent to said light emitting layer.

24. (new): A flat light source comprising the polymer light emitting device of any one of claims 18 to 20.

AMENDMENT UNDER 37 C.F.R. § 1.111
U.S. Appln. 09/995,814
ATTORNEY DOCKET NO. Q67430

25. (new): A segment display comprising the polymer light emitting device of any one of claims 18 to 20.

26. (new): A dot matrix display comprising the polymer light emitting device of any one of claims 18 to 20.

27. (new): A liquid crystal display comprising the polymer light emitting device of any one of claims 18 to 20 as a back-light.